



WOCA EXTERIOR OIL

INSTRUCTIONS

CLASSIFICATION

Product identifier	WOCA Exterior Oil
Use	For basic treatment and maintenance of new and previously oiled engineered bamboo surfaces outdoor.
Container:	0,75 l, 2,5 l
Consumption:	12-15 m ² /l
Exterior Oil:	available in 10 colours (Natural, Teak, Black, Grey, Walnut, Bangkirai, Larch, Anthracite, White, Red Brown)
Characteristic	<ul style="list-style-type: none">• Water based• Provides a hard-wearing surface• Contains UV-protection• Prevents mold and fungus• Suitable for decking, garden furniture, claddings and sidings.• Fast drying
Supplier's details	WOCA USA

APPLICATION

Application area	For basic treatment and maintenance of new and previously oiled engineered bamboo surfaces such as decks, garden furniture, cladding etc
Result	The special water-based composition of oil components ensures that the product is water dilutable and friendly to the environment. The oil ensures a strong water and dirt repellent surface and protects against mould fungus.
Application	Apply the oil with a brush or roller on to the clean engineered bamboo. Repeat the treatment, if the wood is not saturated after the first treatment. Remove excess oil with a cotton cloth. Surface may be buffed with a pad or a polishing machine.
After care	If necessary use WOCA Exterior Oil.
Maintaining and cleaning	Clean with Exterior Cleaner. Maintain with WOCA Exterior Oil.

PREPARATION

Tools

Brush, cotton cloth and possibly sandpaper.
Clean tools with Solvent.

Please notice:

Risk of self-ignition! Due to the risk of self-ignition it is important that sanding dust and oil wetted cloths are soaked in water and disposed of in a tightly closed container after use.

HOW TO DO



- Clean new engineered bamboo surfaces as well as old surfaces with WOCA Exterior Cleaner before starting the oil treatment.
- Then leave the wood to dry for at least 24 hours so that the humidity is not above 17%. Sand down any rough wood fibers with sandpaper, grit 120.
- Make the application in dry weather only, min. temp. 13°C. Avoid direct sunlight and high temperatures.
- Stir the oil thoroughly before use.
- Apply an EVEN and THIN coat of oil with a brush. Treat the end grain engineered bamboo first. The wet oil may have a white shade. When the water has evaporated after a few minutes, the engineered bamboo will appear oiled.



- Wipe off any excess oil with clean cotton cloths after no more than 5 minutes. Take particular care of removing excess oil from joints and grooves.
- If the surface does not appear saturated with oil, repeat steps 5 and 6.
- When the engineered bamboo is dry, it may be polished with a polishing pad or polishing machine to ensure an extra hard-wearing surface.
- It takes 24 to 48 hours for the oil to harden thoroughly, depending on weather conditions and outdoor temperature. The engineered bamboo must not be exposed to water during this period.

CONTACT US

Phone:	Local or Interstate: 1300 665 703 International: (+61)2 9666 5703
For General Enquiries	info@houseofbamboo.com.au
For any Upcoming Projects	projects@houseofbamboo.com.au
Address	Sydney Head Office & Showroom 13 Erith Street, Botany NSW 2019 Brisbane Showroom - Brisbane Design Centre 66 Merivale Street South Brisbane QLD 4101
Opening Hours	Monday to Friday: 8:00am - 4:00pm Saturday: By Appointment Only Sunday: Closed
Website	houseofbamboo.com.au
Follow Us on Instagram	@house.of.bamboo.australia

